

Honest General Trading SRL
CIF: RO 6615609
Reg.Com: J40/25279/1994
Capital Social: 7.050
Sediu Social: Str. Agricultori nr.121,
Sector 3, București



PARAMETRI LIPIRE TEAVA PPR

Diametru Exterior (mm)	Timp de incalzire (sec)	Timp de imbinare (sec)	Timp de racire (min)	Lungimea sudurii (mm)
20	5	4	2	16
25	7	4	3	18
32	10	6	4	20
40	12	6	4	22

Aparatul de sudura trebuie incalzit la o temperatura de aproximativ 260 de grade Celsius